

Main components:

Delivery form / Colour: /

Form of preparation:

Print parameters:

Parameter	Typical values
Softening temperature	°C
Melting temperature	from °C
Printing temperature	°C
Print bed temperature	°C
Heat deflection temperature of printed parts	up to °C
Bulk weight	g/l

Application properties:

Application examples:



Storage:

Toxicity: Not a hazardous mixture according to Regulation (EC) No 1272/2008.

Food contact: Declaration of conformity according to Regulation (EU) No. 10/2011
Annex IV not possible.

Packaging:

Dangerous goods property: no

Status: 000/0524

Unsere technischen Daten stützen sich auf sorgfältige Untersuchungen und stellen unseren aktuellen Erkenntnisstand dar. Dennoch sollen sie nur unverbindlich beraten.

Our technical information is based on careful examinations and is believed to be reliable, but is presented without guarantee.

kcd Kunststoffe, Additive und Beratung GmbH, D-99427 Weimar, Otto-Schott-Str. 5

Tel.: +49 (0) 3643 404837

Fax: +49 (0) 3643 404838

e-mail: info@kcd-additive.com

web: www.kcd-additive.com